






| RATING             | EXAMPLE WEAPON                                                                      | AMMUNITION                                                                       | VELOCITY (FPS)             | TYPICAL SHOT PATTERN/SAMPLE                                                                                                                                                                             | COMPLIANT PRODUCTS                                                                                                                               |
|--------------------|-------------------------------------------------------------------------------------|----------------------------------------------------------------------------------|----------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Level I</b>     |    | (5) .38 Special 158 Round nose lead                                              | 800-900<br>[244-274 m/s]   |                                                                                                                      |                                                                                                                                                  |
|                    |    | (5) .22LR High velocity lead                                                     | 1010-1090<br>[308-332 m/s] |                                                                                                                                                                                                         |                                                                                                                                                  |
| <b>Level II-A</b>  |    | (5) .357 Magnum 158 Grain jacketed lead soft point                               | 1200-1300<br>[366-396 m/s] |                                                                                                                                                                                                         | Glass/Polycarbonate: ARMORGARD® 88" [22mm] SP188 All Glass: ARMORGARD® 94" [24mm]                                                                |
|                    |    | (5) 9mm 124 Grain FMJ lead core                                                  | 1050-1130<br>[320-344 m/s] |                                                                                                                                                                                                         | Glass/Glass FE/BR: CHILDGARD-2118 .527" [14mm]<br>BRN2A94 (test size non-typical)                                                                |
| <b>Level II</b>    |    | (5) .357 Magnum 158 Grain jacketed lead soft point                               | 1345-1445<br>[410-440 m/s] |                                                                                                                      | Glass/Glass FE/BR: CHILDGARD-2118 .527" [14mm]                                                                                                   |
|                    |  | (5) 9mm 124 Grain FMJ lead core                                                  | 1135-1215<br>[346-370 m/s] |                                                                                                                                                                                                         |                                                                                                                                                  |
| <b>Level III-A</b> |  | (5) .44 Magnum 240 Grain lead semi-wadcutter gas checked                         | 1350-1450<br>[411-441 m/s] |                                                                                                                                                                                                         | All Plastic: LEXGARD® 1.25" [32mm] SP1250<br>Glass/Polycarbonate: 1.2" [30mm] SP412<br>Glass/Glass FE/BR: ARMORGARD® Ultimate 1.3" [33mm] SP3A13 |
|                    |  | (5) 9mm 124 Grain FMJ lead core                                                  | 1350-1450<br>[411-441 m/s] |                                                                                                                                                                                                         |                                                                                                                                                  |
| <b>Level III</b>   |  | (5) 7.62mm/308 150 Grain rifle lead core full metal copper jacket, military ball | 2700-2800<br>[823-853 m/s] | Typical Test size, NIJ 0108.01 requires sampling to be at least 12x12" and no space hits as evenly as possible.<br> | Glass/Polycarbonate: ARMORGARD® 1.6" [41mm] SPN316                                                                                               |
| <b>Level IV</b>    |  | (1) .30-06 166 Grain Armor Piercing                                              | 2800-2900<br>[853-883 m/s] | <br>NIJ 0108.01 requires sampling to be at least 12x12"                                                             | Glass/Polycarbonate: ARMORGARD® 2.19" [56mm] SPN420                                                                                              |



The information in this chart is for general reference only; contact your Isoclima representative for additional details or specific inquiries.

Rev: June 2026

 [isoclimagroup.com](https://www.isoclimagroup.com)  
 [info@isoclimagroup.com](mailto:info@isoclimagroup.com)  
 866-412-6977